MATERIAL SAFETY DATA SHEET

Print name: Friday June 16th 2017

Product name

Brown Corundum

Manufacturer

ZHENGZHOU HAIXU ABRASIVES CO.,MLTD http://www.cnhxabrasive.com Room1903,Yaxing times Plaza,Erqi District,Zhengzhou City,Henan Province,China Telephone:+86-371-60305639 Fax:+86-371-60305637

Emergency Telephone Number +86-15738804602

Composition/information on ingredients

•	
Alpha Alumina	95-100%
Titanium Dioxide	17-3.4%
CAS-NO	1344-28-1
EC-NO:	251-691-6

Hazards identification

Not hazardous. The product is inert, so it does not form any explosive or flammable blend. As with all dusts, inhalation should be avoided.

First-aid measures

First Aid – Eyes	Treat symptomatically for mechanical irritation. Flush lightly with clean water.
First Aid – Skin	Powder may cause drying of the skin with repeated or prolonged contact. Wash with soap and water.
First Aid – Ingestion	Rinse mouth out with water.
First Aid – Inhalation	Temporary discomfort to upper respiratory tract may occur due to inhalation of high dust levels. Remove to fresh air.

If any symptoms develop, seek medical aid.

Fire-fighting measures

Non flammable and not explosive - no special precautions necessary. Skin Contact

Accidental release measures

Collect dry powder using a vacuum cleaner or other means where dust is not generated.

Handling and storage

Handling	Appropriate controls should be used to avoid generating dust when
	handling dry powders.
Storage	Powders should be stored at ambient temperature in a dry covered area.
	The product should be stored in sealed bags, away from humidity in a
	well ventilated area if possible.

Exposure controls/Personal protection

Respiratory protection	Use appropriate engineering controls to avoid dust generation when handling powders. Ensure that all occupational exposure standards are observed.
Skin protection	Substance may have a drying effect on the skin. Maintain good standards of industrial hygiene.
Eye protection	Eyewash should be available, eye protection is recommended.

Physical and Chemical Properties:

Physical and chemical properties	
Form:	powder
Odour:	odourless
Melting point	NA
Boiling point:	NA
Explosive properties	None
Relative density	2.55

Stability and reactivity

, <u>,</u>	
Conditions to avoid	Protect against moisture
Material to avoid	None known
Hazardous decomposition products	None known

Toxicological information

Inhalation	Temporary discomfort or mechanical irritation to the upper respiratory		
	tract may occur due to inhalation of high dust concentrations. No		
	acute effects expected		
Skin contact	No determined toxicological effects.		
Ingestion	No determined toxicological effects.		

Ecological information

Environmental Statement brown Corundum is persistent and non-biodegradable but is unlikely to have any long term effect on the environment.

Mobility	olid. Involatile. Insoluble in water
Degradability	Non-biodegradable. Persistent.
Accumulation	No bio-accumulation or bio-magnification identified.

Waste disposal information

brown Corundum may be disposed of as non toxic/inactive materials in approved landfill sites in accordance with local regulations.

Transport information

brown corundum is not classified as dangerous for transportation under EU or UK national regulations. No special precautions are required.

UN number	ADR/RID:	IMDG:-	IATA:
UN proper sl	hipping nar	ne	
ADR/RID: Not	t dangerous	goods	
IMDG: Not da	angerous go	ods	
IATA: Not dan	igerous goo	ds	
Transport ha	zard class(e	es)	
ADR/RID: -	IMDG:-	IATA:-	
Packaging g	roup		
ADR/RID: -	IMDG:-	IATA:-	
Environmental hazards			
ADR/RID: no	IMDG:-	IATA:-no	
Special preca	autions for	user	
No data available			

Regulatory information

brown corundum is not classified as dangerous to supply under EU or UK national regulations.

Other information

The information provided in this safety data sheet is correct to the best of our knowledge information and belief at the date of its publication. The information given is designed only as a guidance for safe handling, use, postrecession, storage, transmigration, disposal and release and is not to be considered a warranty or quality specification. The information relates only to the specific material designated and is not valid for sun material used in combination with any other materials or in any process.