ZHENGZHOU HAIXU ABRASIVES CO.,LTD EMAIL:SALES@ZZHAIXU.CN MP/WECHAT/WHATSAPP:+8615838373120 WEBSITE:http://hbfa.net

## **TECHNICAL DATA SHEET**

## **PRODUCT:** BROWN FUSED ALUMINA

**SIZE**:P280

Brown Fused Alumina is made from Calcined Bauxite. It is a hard and tough material, used in grinding wheels manufacturing (both vitrified and resin bonded) and coated products. These grains are also used for shot blasting and as polishing media.

AVERAGE CHEMICAL COMPOSITION(TYPICAL)		<u>PHYSICAL PROPERTIES(TYPICAL)</u>	
$Al_2O_3$	93.5-97.5%	Specific Gravity	≥3.90g/cm <sup>3</sup>
TiO <sub>2</sub>	1.7-3.4%	Mohs Hardness	9.0
Fe <sub>2</sub> O <sub>3</sub>	≤0.50%	<b>Bulk Density</b>	1.53-1.99g/cm <sup>3</sup>
SiO <sub>2</sub>	≤2.00%	Melting Point	2250°C
CaO	≤0.50%	Refractoriness	1900°C

## **PARTICLE SIZE DISTRIBUTION**

<b>STANDARD</b>	VALUE	(um)
JIMIDMID	VALUE	ulli

D0	≤101
D3	≤74.0
D50	52.2±2.0
D95	≥39.2

## **MAIN APPLICATIONS**

- -Bonded Abrasives and Coated abrasives
- -Wet and dry blast media, grinding and polishing etc
- -PCB plate(PCBA,FPC,LED) blasting
- -Polishing wax, Grinding stones, polishing pads etc
- -removal of scale, rust and old coatings
- -ceramics shapes
- -Grinding wheels, Cup wheels etc
- -brake and friction linings

••

PACKAGING: 25kgs PVC bags+1MT big bag/pallet

The shown values are typical characteristics of the material and shall not be used to prepare specifications. They are submitted to tolerances of the production and meet the present standard of technique. We reserve our right for changes within the scope of technical progress or internal improvement..